

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C07C 5/13, 5/33, B01J 29/32	A1	(11) International Publication Number: WO 91/00851 (43) International Publication Date: 24 January 1991 (24.01.91)
(21) International Application Number: PCT/US90/03655 (22) International Filing Date: 25 June 1990 (25.06.90) (30) Priority data: 376,972 6 July 1989 (06.07.89) US (71) Applicant: CHEVRON RESEARCH AND TECHNOLOGY COMPANY [US/US]; Post Office Box 7141, San Francisco, CA 94120-7141 (US). (72) Inventor: HOLTERMANN, Dennis, L. ; 576 Standard Avenue, Richmond, CA 94802 (US). (74) Agents: DE JONGHE, Thomas, G. et al.; Chevron Corporation, Post Office Box 7141, San Francisco, CA 94120-7141 (US).		(81) Designated States: AT (European patent), AU, BB, BE (European patent), BG, BR, CA, CH (European patent), DE (European patent)*, DK, DK (European patent), ES (European patent), FI, FR (European patent), GB (European patent), HU, IT (European patent), JP, KP, KR, LK, LU (European patent), MC, MG, MW, NL (European patent), NO, RO, SD, SE (European patent), SU. Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: ISOMERIZATION CATALYST AND PROCESS FOR ITS USE (57) Abstract The present invention is a process and a catalyst for isomerizing normal and slightly branched C ₄ to C ₇ hydrocarbons. The catalyst comprises a Group VIII metal on Beta zeolite.		

DESIGNATIONS OF "DE"

Until further notice, any designation of "DE" in any international application whose international filing date is prior to October 3, 1990, shall have effect in the territory of the Federal Republic of Germany with the exception of the territory of the former German Democratic Republic.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	ES	Spain	MC	Monaco
AU	Australia	FI	Finland	MG	Madagascar
BB	Barbados	FR	France	ML	Mali
BE	Belgium	GA	Gabon	MR	Mauritania
BF	Burkina Faso	GB	United Kingdom	MW	Malawi
BG	Bulgaria	GR	Greece	NL	Netherlands
BJ	Benin	HU	Hungary	NO	Norway
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	SD	Sudan
CF	Central African Republic	KP	Democratic People's Republic of Korea	SE	Sweden
CG	Congo	KR	Republic of Korea	SN	Senegal
CH	Switzerland	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
DE	Germany, Federal Republic of	LU	Luxembourg	TC	Togo
DK	Denmark			US	United States of America

-1-

01

ISOMERIZATION CATALYST AND PROCESS FOR ITS USE

05

FIELD OF THE INVENTION

The present invention is a process for alkane isomerization. More specifically, the present invention is a process for isomerizing C₄ to C₇ paraffins to increase their octane rating.

10

BACKGROUND OF THE INVENTION

The petroleum distillate fraction that contains C₄ to C₇ hydrocarbons is relatively low in octane because it contains substantial amounts of low octane, normal paraffins. For example, normal C₅ has a blending RON of 62 and normal C₆ has a blending RON of 19 (blending RON will be hereinafter called "RON"). However, when these paraffins are isomerized to form branched paraffins, their RON increases dramatically. For example, isopentane (2-methylbutane) has a RON of 99 and isohexane (2-methylpentane) has a RON of 83. Generally, the RON will increase with even higher branching (e.g., 2,2-dimethylbutane has a RON of 89).

20

Several catalysts have been used to isomerize these lower octane paraffins into the branched, higher octane paraffins. Examples are shown in U.S. Patent No. 4,374,296 issued February 15, 1983 to Haag et al.; U.S. Patent No. 3,432,568 issued March 11, 1969 to Miale et al.; U.S. Patent No. 3,673,267 issued June 27, 1972 to Chen et al.; and U.S. Patent No. 4,665,272 issued May 12, 1987 to Bakas et al. Haag et al. disclose isomerizing paraffins using intermediate pore zeolites, which have a constraint index between 1 and 12. Miale et al. describe hydroisomerizing saturated aliphatic and cyclic hydrocarbons by contacting them with a dual functional catalyst comprising mordenite and a catalytic metal. Chen et al. describe a process for isomerizing paraffins using mordenite having a silica to alumina ratio between 20:1 and 60:1. Bakas et al. disclose isomerizing paraffins using a crystalline aluminosilicate having a catalytic metal.

30

35

40

-2-

01

05

However, even though these prior art catalysts are useful, there remains a need for a new catalyst that is: (1) highly active; (2) highly selective for producing high octane liquid product; and (3) sulfur tolerant. That need is satisfied by the invention that is detailed below.

SUMMARY OF THE INVENTION

10

15

20

According to the present invention, a catalyst and a process for using the catalyst are provided for isomerizing C₄ to C₇ hydrocarbons. The catalyst comprises a Group VIII metal and Beta zeolite and the process comprises contacting the catalyst with a feed having normal and branched C₄ to C₇ hydrocarbons under isomerization conditions. Preferably, the Group VIII metal is platinum and the feed substantially comprises normal and singly branched lower octane C₅ and C₆ hydrocarbons. To improve catalytic activity the catalyst is preferably calcined in a steam/air mixture at an elevated temperature after impregnation with the Group VIII metal.

25

Among other factors, the present invention is based on my finding that a catalyst comprising Beta zeolite and a Group VIII metal is highly active and highly selective for isomerizing C₅ and C₆ hydrocarbons. The catalyst is also surprisingly selective for isomerizing C₇ hydrocarbons. Additionally, the catalyst is relatively sulfur tolerant. Furthermore, when the catalyst is calcined in a steam/air mixture, higher activity and selectivity are achieved.

30

35

More specifically, the process for alkane isomerization comprises contacting a feed containing low octane normal and singly branched C₅ and C₆ hydrocarbons and less than 0.1 ppm sulfur with a catalyst which comprises Beta zeolite and between 0.1% and 1.0% platinum, at a temperature between 400°F and 600°F, at a pressure between 100 and 500 psig, a H₂/HC ratio between 1 and 8, and between 1 and 4 LHSV.

DETAILED DESCRIPTION OF THE INVENTION

40

The following discussion presents a more detailed discussion of the present catalyst.

01

-3-

The Catalyst

05 Beta zeolite is a large pore zeolite. Large pore zeolites typically have effective pore diameters between 6 and 8 Angstroms (\AA). Beta zeolite has a pore opening of approximately 7 \AA . Although its present structure is unknown, it is believed to have pore windows formed by twelve-membered rings of silicon and aluminum atoms.

10

 Beta zeolite is substantially shown and described in U.S. Patent No. 3,308,069 and Re 28,341 to Wadlinger et al., and Breck, "Zeolite Molecular Sieves", p. 309 (1984), which are all hereby incorporated by reference in their entireties. These references describe a process for making Beta zeolite, its elemental composition and formula.

15

 Preferably, the Beta zeolite of the present invention has a silica to alumina molar ratio between 10 and 1000, more preferably between 15 and 100. It is also preferable that the catalyst have high acidity. The catalyst's acidity can be increased by ammonium ion exchange and subsequent calcination to yield the hydrogen form. In addition to the hydrogen form, other forms of the zeolite can be used if they are sufficiently acidic. Preferably, the catalyst is substantially free of alkali or alkaline earth metals.

20

25

 Preferably, catalysts of the present invention contain one or more Group VIII metals, e.g., nickel, ruthenium, rhodium, palladium, iridium or platinum. The preferred Group VIII metals are iridium, palladium, and most preferably platinum. The preferred percentage of the Group VIII metal in the catalyst is between 0.05% and 5%, more preferably between 0.1% and 2.5%, most preferably between 0.1% and 1.0%.

30

35

 Group VIII metals are preferably introduced into Beta zeolite by impregnation, occlusion, or exchange in an

01

05

aqueous solution of an appropriate salt. When it is desired to introduce two Group VIII metals into Beta zeolite, the operation may be carried out simultaneously or sequentially. Preferably, the Group VIII metal is highly dispersed within, and on, the zeolite.

10

15

By way of example, platinum can be introduced by impregnation with an aqueous solution of tetraammineplatinum (II) nitrate, tetraammineplatinum (II) hydroxide, dinitrodiamino-platinum or tetraammineplatinum (II) chloride. In an ion exchange process, platinum can be introduced by using cationic platinum complexes such as tetraammineplatinum (II) nitrate. On the other hand, when platinum is introduced into the zeolite by occlusion a platinum complex is preferably introduced into the zeolite during its synthesis.

20

After the desired metal or metals have been introduced, the catalyst is preferably calcined in air, or air diluted with an inert gas. More preferably, the catalyst is calcined in a steam/air mixture at an elevated temperature after platinum impregnation.

25

Promoter metals can be added to the catalyst in the manner described above. These metals are preferably selected from Groups VIII, IVA, IB or VIB.

30

35

The zeolite is preferably bound with a porous matrix. The term "porous matrix" includes inorganic compositions with which the zeolite will effectively bond after appropriate thermal treatment. The matrix porosity can either be inherent or it can be introduced by chemical means. Satisfactory matrices include pumice, firebrick, diatomaceous earth and inorganic oxides. Preferred inorganic oxides include alumina, silica, naturally occurring or synthetic clays (for example, bentonite, kaolin, sepiolite, attapulgite, and halloysite). Silica or alumina are especially preferred.

40

Compositing the zeolite with an inorganic oxide matrix can be achieved by any suitable known method wherein the zeolite is intimately admixed with the oxide while the latter is in a hydrous state (for example, as a

01

-5-

hydrous salt, hydrogel, wet gelatinous precipitate, or in
a dried state, or combinations thereof). A convenient
05 method is to prepare a hydrous mono or plural oxide gel or
cogel using an aqueous solution of a salt or mixture of
salts (for example, sodium silicate). Ammonium hydroxide
(or a similar base) is added to the solution in an amount
sufficient to precipitate the oxides in hydrous form.
10 Then, the precipitate is washed to remove most of the
water soluble salts and it is thoroughly admixed with the
zeolite which is in a finely divided state. Water or
lubricating agents can be added in an amount sufficient to
facilitate shaping of the mix (e.g., by extrusion).

15 The Process

Once the catalyst has been formed it can be
employed in any of the conventional types of process
equipment known to the art. It may be employed in the
form of pills, pellets, granules, broken fragments, or
20 various special shapes. It can be disposed as a fixed
or moving bed within a reaction zone, and the charging
stock can be passed therethrough as a liquid, vapor, or
mixed phase, and in upward, downward, or radial flow.
Alternatively, it could be prepared for use in fluidized-
25 solid processes, in which the charging stock is passed
upward through a turbulent bed of finely divided catalyst.
However, in view of the danger of attrition losses of the
valuable catalyst and the well-known advantages of plug
flow reactors either a fixed bed system or a dense-phase
30 moving bed system is preferred. In a fixed bed system,
the feed is preheated (by any suitable heating means) to
the desired reaction temperature and then passed into a
isomerization zone containing the catalyst. This isomer-
ization zone may be one or more separate reactors with
35 suitable means to maintain the desired temperature at the
entrance to each reactor. After reaction, the products
from any of the foregoing process variants are separated
from the catalyst, reduced to atmospheric pressure, and
fractionated to recover the various components thereof.
40 Additionally, the process can be operated in once-through

-6-

01

or, preferably, with recycle of normal paraffins. Recycle operations are within the knowledge of skilled practitioners.

05

As discussed above, the petroleum distillate fraction preferably contains normal and singly branched C_4 to C_7 Paraffins. The feed preferably contains few multiply branched components such as 2,2-dimethylbutane and 2,3-dimethylbutane. However, when the low octane paraffins are isomerized to form multiply branched paraffins (such as the dimethylbutanes, for example), the octane number increases dramatically. This is the function of the present catalyst.

10

15

The present catalyst is highly active and highly selective for isomerizing C_4 to C_7 hydrocarbons. This high selectivity means that in comparison to prior art catalysts, such as mordenite, a higher product yield can be achieved when the two catalysts are run to a given octane. It also means that a higher octane can be achieved when the two catalysts are run to produce a given liquid yield.

20

The present process comprises contacting the isomerization catalyst with a hydrocarbon feed under isomerization conditions. The feed is preferably a light straight run fraction, boiling within the range of 30°F to 250°F and preferably from 60°F to 200°F. Preferably, the hydrocarbon feed for the process comprises a substantial amount of C_4 to C_7 normal and singly branched hydrocarbons, more preferably low octane C_5 and C_6 hydrocarbons.

25

30

The pressure in the process is preferably between 50 psig and 1000 psig, more preferably between 100 and 500 psig. The liquid hourly space velocity (LHSV) is preferably between about 1 to about 10 with a value in the range of about 1 to about 4 being more preferred. It is also preferable to carry out the isomerization reaction in the presence of hydrogen. Preferably, hydrogen is added to give a hydrogen to hydrocarbon ratio (H_2/HC) of between 0.5 and 10, more preferably between 1 and 8. The temperature is preferably between about 200°F and about 1000°F, more preferably between 400°F and 600°F. As is well known

35

40

-7-

01

05

10

15

20

25

30

35

to those skilled in the isomerization art, the initial selection of the temperature within this broad range is made primarily as a function of the desired conversion level considering the characteristics of the feed and of the catalyst. Thereafter, to provide a relatively constant value for conversion, the temperature may have to be slowly increased during the run to compensate for any deactivation that occurs.

The present catalyst is relatively sulfur tolerant. Nonetheless, a low sulfur feed is especially preferred in the present process. The feed preferably contains less than 10 ppm, more preferably less than 1 ppm, and most preferably less than 0.1 ppm sulfur. In the case of a feed which is not already low in sulfur, acceptable levels can be reached by hydrotreating the feed in a pretreatment zone with a hydrotreating catalyst which is resistant to sulfur poisoning. Sulfur can be subsequently removed as hydrogen sulfide in the gas phase after condensation of the liquid product. An example of a suitable catalyst for this hydrodesulfurization process is an alumina-containing support and a minor catalytic proportion of molybdenum oxide, cobalt oxide and/or nickel oxide. Hydrodesulfurization is typically conducted at 315°C to 455°C, at 200 to 2000 psig, and at a liquid hourly space velocity of 1 to 5.

It is also preferable to limit the nitrogen level and the water content of the feed. Catalysts and processes which are suitable for these purposes are known to those skilled in the art.

After a period of operation the catalyst can become deactivated by sulfur or coke. Sulfur and coke can be removed from the catalyst using procedures that are known to those skilled in the art.

The present invention will be more fully understood by reference to the following examples. They are intended to be purely exemplary and are not intended to limit the scope of the invention in any way.

40

-8-

01

EXAMPLESExample 1

05 In a 2-liter glass liner, 8.29 gms of Mallinkrodt sodium aluminate ($\text{Na}_2\text{O} \cdot \text{Al}_2\text{O}_3 \cdot 3\text{H}_2\text{O}$) was dissolved in 259.6 gms of an aqueous solution containing 20% tetraethyl ammonium hydroxide (Aldrich). 207.5 Grams of Ludox AS-30 colloidal silica was added in a thin stream while the solution was vigorously stirred. The liner was placed in a 2-liter Parr stainless steel bomb and statically heated for 6 days at 150°C. The solid, precipitate product was washed and dried, after which it was determined to be Beta zeolite by X-ray diffraction.

15 Beta zeolite was made more catalytically active by converting it into its hydrogen (proton) form as follows. Beta zeolite was layered in a thin bed and incrementally heated to 1000°F at a rate of 150°/hr. The temperature was maintained at 1000°F for 5 hours and then it was increased to 1100°F for 4 more. The calcined zeolite was ion-exchanged by 4 successive treatments with NH_4NO_3 . Each treatment used the same mass of NH_4NO_3 to zeolite (a slurry of about 50 gr. zeolite/liter H_2O) and the solution was refluxed for at least 2 hours. The sodium content of the zeolite was low after the fourth exchange. The zeolite was filtered, washed, dried and recalined as above while omitting the 1100°F heating step.

25 The final Beta zeolite was impregnated with enough tetraamine platinum nitrate to achieve 0.8 wt.% platinum. Thereafter, the impregnated catalyst was dried at 250°F for approximately 14 hours then calcined at 500°F for 3 hours, and then reduced.

Example 2

35 The catalyst of Example 1 was used to isomerize a feed which substantially comprised normal and branched C_5 and C_6 hydrocarbons. The isomerization conditions were 1 LHSV, 200 psig, 6 H_2/HC , and 520°F. The feed composition and the isomerization results are shown in Table I.

40

01

-9-

TABLE I

	Compound (Wt.%)	Feed	Isomerate
05	Methane	0.00	0.00
	Ethane	0.00	0.00
	Propane	0.00	0.71
	Isobutane	0.04	1.84
	N-butane	0.28	0.64
10	Iso-C ₅	12.03	21.45
	N-pentane	18.93	11.37
	2,2-DMB	0.58	9.56
	Cyclo-C ₅	4.26	3.69
	2,3-DMB	2.26	4.44
	2MP	12.55	15.36
	3MP	8.19	10.11
15	N-hexane	19.74	8.46
	MCP	15.04	9.82
	Benzene	3.75	0.00
	CHX	1.89	2.56
	C ₇ +	0.45	0.00
	C ₅ + Wt.%	99.68	96.81
20	LV%	100.00	99.01
	RON	74.50	80.08

Example 3

A commercial mordenite (Zeolon 100H) was obtained from Norton Chemical Company and platinum impregnated as in Example 1. The final catalyst contained 0.8 wt.% platinum.

Example 4

This example compares the liquid yields achievable with the catalysts of Example 1 and Example 3, which both contained 0.8% platinum.

Both catalysts were used to isomerize normal C₅, C₆, and C₇ pure component feeds at 500°F, 100 psig, and 6H₂/HC. The liquid yields and corresponding octanes that were obtained for the two catalysts are shown in FIG. 1.

Example 5

Platinum was impregnated onto samples of Beta zeolite and mordenite at varying levels. Both catalysts were used to isomerize a normal hexane feed at 510°F, 100 psig, 3 LHSV, and 6H₂HC. The results are shown in

-10-

Table II. The relative intrinsic activity for each catalyst at low conversion was calculated and is shown in FIG. 2.

TABLE II

Catalyst Support	Pt	nC ₆ Conv.	LV%	Isomerase RON
H-Beta	2.4	84	94	76.0
	0.8	83	97	76.1
	0.05	82	98	75.3
H-Mordenite	2.4	80	92	74.1
	0.8	82	95	75.1
	0.05*	76	90	64.5

*Temp. raised to 540°F due to low activity.

Example 6

This example demonstrates the effect of sulfur on platinum/Beta zeolite and platinum/mordenite catalysts. Each catalyst was contacted with the feed of Table I at 520°F, 200 psig, 6H₂HC, and 1 LHSV for 24 hours. Then H₂S was continuously added to the reactor inlet H₂ and into the feed for 24 hours. The H₂S addition rate was sufficient to give approximately 250 ppm sulfur on a feed weight basis. Thereafter, the H₂S was removed and the catalysts were only contacted with clean feed and clean hydrogen. The results are shown in Table III.

TABLE III

Catalyst	Time	ppm Sulfur (Feed Wt. Basis)	Yield (LV%)	RON (Calc.)
0.3% Pt on Mordenite	0-24	0	95.3	79.9
	24-48	234	86.5	80.2
	48-72	0	95.2	79.7
0.3% Pt on Beta Zeolite	0-24	0	97.5	79.7
	24-48	234	95.3	79.7
	48-72	0	97.3	79.2

-11-

01

05

The conventional platinum on mordenite catalyst suffers a relatively larger loss in liquid yield than platinum on Beta zeolite catalyst. Additionally, when sulfur is withdrawn, both catalysts recover from sulfur poisoning, but the liquid yield from the platinum/Beta zeolite is relatively higher.

Example 7

10

This example demonstrates a preferred method of platinum loading which includes a steam calcination step after platinum impregnation.

15

Beta zeolite was prepared in the manner set forth in Example 1. Platinum was impregnated onto the Beta zeolite to achieve 0.3 wt.% and then samples of the catalyst were subjected to different calcination treatments. The different catalysts were then used to isomerize the feed of Table I at 200 psig, 1 LHSV, 6 H₂/HC, for 20 hours. The results are shown in Table IV.

20

TABLE IV

Catalyst	Calcination Conditions	Reaction Temperature	Isomerate Properties			
			i/nC ₅	2,2-DMB/nC ₆	Yield (LV%)	RON (Calc.)
0.3% Pt/ Beta	500°F in Air	520°F	1.7	0.6	97.4	79.5
0.3% Pt/ Beta	500°F in 50% Steam/ 50% Air	515°F	1.8	1.0	97.8	79.9
0.3% Pt/ Beta	600°F in 50% Steam/ 50% Air	520°F	2.1	0.9	97.0	80.1

35

When the catalysts were calcined in a steam/air mixture, the product ratios of iso to normal C₅ hydrocarbons (i/nC₅) and 2,2-dimethylbutane to normal C₆ hydrocarbons (2,2-DMB/nC₆) increased, which in turn increased the product RON. Additionally, this increase was achieved at

40

-12-

01

a lower reaction temperature which indicated an increase in catalyst activity.

05

10

The embodiments of this invention which are exemplified above are intended solely as illustrations of the invention. They should not be interpreted as limiting the scope of the invention to just those features which are shown or disclosed. As those familiar with this area of research will appreciate, there are numerous variations of the invention as defined in the following claims which may have not been exemplified but which will achieve equivalent results.

15

20

25

30

35

40

01

-13-

WHAT IS CLAIMED IS:

- 05 1. A process for isomerizing C_4 to C_7 hydrocarbons, comprising contacting a catalyst, comprising at least one Group VIII metal and Beta zeolite, with a feed having C_4 to C_7 hydrocarbons under isomerization conditions.
- 10 2. A process in accordance with Claim 1 wherein the catalyst has been calcined in a steam/air mixture at an elevated temperature after impregnation of the Group VIII metal.
- 15 3. A process in accordance with Claim 1 wherein the Group VIII metal is platinum.
4. A process in accordance with Claim 3 wherein the catalyst comprises between 0.05% and 5% platinum.
- 20 5. A process in accordance with Claim 3 wherein the catalyst comprises between 0.01% and 2.5% platinum.
- 25 6. A process in accordance with Claim 1 wherein the feed comprises normal and singly branched C_5 and C_6 hydrocarbons.
- 30 7. A process in accordance with Claim 6 wherein the temperature is between 200°F and 1000°F, the pressure is between 50 and 1000 psig, the LHSV is between 1 and 10, and a H_2/HC ratio between 0.5 and 10.
- 35 8. A process for alkane isomerization, comprising: contacting a feed containing normal and singly branched C_5 and C_6 hydrocarbons with a catalyst, which comprises Beta zeolite and between 0.1% and 1.0% platinum, at a temperature between 400°F and 600°F, at a pressure between 100 and 500 psig, a H_2/HC ratio between 1 and 8, and between 1 and 4 LHSV.

40

01

-14-

9. A process for alkane isomerization, comprising:
contacting a feed containing normal and singly branched C₅
05 and C₆ hydrocarbons and less than 0.1 ppm sulfur with a
catalyst, which comprises Beta zeolite and between 0.1%
and 1.0% platinum, at a temperature between 400°F and
600°F, at a pressure between 100 and 500 psig, a H₂/HC
ratio between 1 and 8, and between 1 and 4 LHSV.

10

10. An alkane isomerization catalyst for isomerizing
C₄ to C₇ hydrocarbons, comprising a Group VIII metal and
Beta zeolite wherein the catalyst has been calcined in a
steam/air mixture at an elevated temperature after
15 impregnation with the Group VIII metal.

11. A catalyst in accordance with Claim 10 wherein
the Group VIII metal is platinum.

20

12. A catalyst in accordance with Claim 11 wherein
the catalyst comprises between 0.05% and 5% platinum.

13. A catalyst in accordance with Claim 12 wherein
the catalyst comprises between 0.1% and 2.5% platinum.

25

14. A catalyst in accordance with Claim 10 wherein
the Beta zeolite has a silica to alumina ratio between 15
and 100.

30

35

40

1/2




FIG. 1.

2/2




FIG. 2.

SUBSTITUTE SHEET

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US90/03655

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) *		
According to International Patent Classification (IPC) or to both National Classification and IPC		
IPC (5) : C07C 5/13, 5/33; B01J 29/32		
U.S. Cl : 585/739, 751; 502/66		
II. FIELDS SEARCHED		
Minimum Documentation Searched *		
Classification System	Classification Symbols	
U.S.	585/739, 751; 502/66	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched *		
III. DOCUMENTS CONSIDERED TO BE RELEVANT ¹⁴		
Category *	Citation of Document, ¹⁴ with indication, where appropriate, of the relevant passages ¹⁵	Relevant to Claim No. ¹⁴
Y	US,A 4,642,226 (CALVERT ET AL) 10 February 1987 See column 4, lines 43-68 and columns 5 & 6.	ALL
Y	US,A 4,554,145 (RUBIN) 19 November 1985 See column 6, lines 5-15.	ALL
Y	US,A 4,518,485 (LAPIERRE ET AL) 21 May 1985 See the claims.	ALL
Y	US,A 4,419,220 (LAPIERRE ET AL) 06 December 1983 See column 6, lines 51-68, the paragraph bridging columns 7 & 8, the examples, & the claims.	ALL
(CON'T)		
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p>* Special categories of cited documents: ¹⁵</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"Δ" document member of the same patent family</p> </div> </div>		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search *		Date of Mailing of this International Search Report *
30 AUGUST 1990		06 DEC 1990
International Searching Authority *		Signature of Authorized Official ¹⁶ REC-HO
ISA/US		INTERNATIONAL DIVISION M PATRICK P. GARVIN <i>Ng n Ho Ngayee</i>

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category *	Citation of Document, ¹⁰ with indication, where appropriate, of the relevant passages ¹⁷	Relevant to Claim No ¹⁸
Y	US,A 4,501,926 (LAPIERRE ET AL) 26 February 1985 See the paragraph bridging columns 6 & 7, the paragraph bridging columns 7 & 8, the examples, and the claims.	ALL
Y	USA, 3,308,069 (WADLINGER ET AL) 07 March 1967.	10-14
Y	US,A 4,554,065 (ALBINSON ET AL) 19 November 1985 See the paragraph bridging columns 2 & 3, the paragraph bridging columns 5 & 6 and the examples.	10-14